

The crystal structure of sinkankasite, a complex heteropolyhedral sheet mineral

PETER C. BURNS,* FRANK C. HAWTHORNE

Department of Geological Sciences, University of Manitoba, Winnipeg, Manitoba R3T 2N2, Canada

ABSTRACT

The crystal structure of sinkankasite, $Z = 2$, $\text{Mn}^{2+}(\text{H}_2\text{O})_4[\text{Al}(\text{PO}_3\text{OH})_2(\text{OH})](\text{H}_2\text{O})_2$, triclinic, $a = 9.590(2)$, $b = 9.818(2)$, $c = 6.860(1)$ Å, $\alpha = 108.04(3)$, $\beta = 99.63(3)$, $\gamma = 98.87(3)^\circ$, $V = 590.7(2)$ Å³, space group $P\bar{1}$, has been solved by direct methods and refined to an R index of 7.2% and an R_w index of 7.6% using 2170 unique observed reflections ($|F_o| \geq 5\sigma_F$) collected with MoK α X-ray radiation. The structure contains one distinct Mn^{2+} position, which is octahedrally coordinated by two O atoms and four H_2O groups. There are two distinct Al positions; each is octahedrally coordinated by four O atoms and two OH groups. The two distinct P positions are each tetrahedrally coordinated by three O atoms and one OH group. There are 15 unique H positions, which have been located and refined using soft constraints.

The structure consists of corner-sharing chains of $\text{Al}\phi_6$ octahedra, decorated on both sides by $\text{P}\phi_4$ tetrahedra. These heteropolyhedral chains are linked through the $\text{Mn}\phi_6$ octahedra to form continuous sheets of composition $\text{MnAlP}_2\text{O}_6(\text{OH})_3 \cdot 4\text{H}_2\text{O}$. There are two interlayer anion positions, both of which are occupied by H_2O groups. There are eight unique H bonds between the interlayer cations and the sheets on either side, and no other bonding occurs between the sheets. A total of seven unique H bonds occur between anions of the same heteropolyhedral sheet.

INTRODUCTION

Sinkankasite was described as $\text{H}_2\text{MnAl}(\text{PO}_4)_2(\text{OH}) \cdot 6\text{H}_2\text{O}$ by Peacor et al. (1984). It occurs in the Barker pegmatite, South Dakota, as an alteration product of triphylite, where it is associated with other secondary phosphates, including vivianite, hureaulite, carbonate-apatite, strengite, barboselite, and fluellite. Sinkankasite is multiply twinned by reflection on $\{100\}$. However, because sinkankasite is triclinic, there is only random overlap of reflections in reciprocal space (except for those occurring on the twin plane, i.e., $\{0kl\}$ reflections). Hence single-crystal intensity data can be collected from one component of the twinned crystal if the cell of this component can be oriented. We have determined the crystal structure of sinkankasite in this fashion and report the results here.

EXPERIMENTAL METHODS

A small tabular crystal fragment of sinkankasite from the Barker pegmatite, near Keystone, Pennington County, South Dakota, was mounted on a Nicolet R3m automated four-circle diffractometer. Twenty-one reflections over the range $4^\circ \leq 2\theta \leq 18^\circ$ were centered using graphite-monochromated MoK α X-radiation. The unit-cell dimensions (Table 1) were derived from the setting angles of the 21 automatically aligned reflections by least-

squares refinement. Data were collected using the θ - 2θ scan method with a 2.3° 2θ scan range and a variable scan rate ranging from 4 to 29.3° $2\theta/\text{min}$. A total of 3650 reflections was measured; the index ranges $0 \leq h \leq 13$, $-13 \leq k \leq 13$, and $-9 \leq l \leq 9$ were covered. Two standard reflections were measured every 50 reflections. There was a gradual decline in their intensities by several percent during data collection; we attribute this decline to crystal deterioration, and the data were scaled based on the standards. We recorded intensity data on a standard ruby crystal immediately after the sinkankasite experiment. There was no significant change in the standard reflections of the ruby crystal during data collection, supporting our assumption that the sinkankasite crystal deteriorated during exposure to the X-ray beam. An empirical absorption correction based on 36 ψ -scans for each of nine reflections over the range $8^\circ \leq 2\theta \leq 54^\circ$ was applied, reducing R (azimuthal) from 10.7 to 4.9%. This agreement index is higher than we normally encounter and is a result of the twinned nature of the crystal (all current absorption-correction routines assume that the data are collected from a single crystal). The data were corrected for absorption, Lorentz, polarization, and background effects; of the 3650 reflections measured, 2170 were classed as observed ($F \geq 5\sigma_F$).

STRUCTURE SOLUTION AND REFINEMENT

Scattering curves for neutral atoms, together with anomalous-dispersion corrections, were taken from

* Present address: Department of Earth Sciences, University of Cambridge, Downing Street, Cambridge CB2 3EQ, U.K.

TABLE 1. Crystallographic data for sinkankasite

<i>a</i> (Å)	9.590(2)	Crystal size (mm)	0.04 × 0.24 × 0.12
<i>b</i> (Å)	9.818(2)	Radiation	MoK α
<i>c</i> (Å)	6.860(1)	Total ref.	3650
α (°)	108.04(3)	$ F \geq 5\sigma_F$	2170
β (°)	99.63(3)	Final <i>R</i>	7.2%
γ (°)	98.87(3)	Final <i>R_w</i>	7.6%
<i>V</i> (Å ³)	590.7(2)		
<i>F</i> ₀₀₀	406	<i>D</i> _{calc}	2.243 g/cm ³
Space group	<i>P</i> $\bar{1}$	μ	1.49 mm ⁻¹
Unit-cell contents 2[Mn ²⁺ (H ₂ O) ₄][Al(PO ₃ OH) ₂ (OH)](H ₂ O) ₂			
$R = \sum (F_o - F_c) / \sum F_o $			
$R_w = [\sum w (F_o - F_c)^2 / \sum w F_o^2]^{1/2}$, $w = 1/\sigma_F^2$			

Cromer and Mann (1968) and Cromer and Liberman (1970), respectively. The Siemens SHELXTL PLUS (PC version) system of programs was used throughout this study. *R* indices are of the form given in Table 1 and are expressed as percentages.

The possible space groups of sinkankasite are *P*1 and *P* $\bar{1}$; reflection statistics favor the latter and the successful solution and refinement of the structure verifies that the space group of sinkankasite is *P* $\bar{1}$. The structure was solved by direct methods, followed by cycles of least-squares refinement and calculation of difference-Fourier maps. Refinement of the positional and isotropic displacement

parameters of the complete model (excluding H positions) gave an *R* index of 13%. Conversion to an anisotropic displacement model, together with refinement of all parameters, gave an *R* index of 7.5%. At this stage of the refinement, a difference-Fourier map was calculated, and the positions of 15 H atoms were determined. Subsequent cycles of refinement showed that the H positions were characterized by anomalously short O-H bond lengths, a common feature of H positions refined using X-ray data. The soft constraint that O-H distances should be ~0.96 Å was imposed by adding extra weighted observational equations to the least-squares matrix. Only the O-H distance is constrained, and each H position is free to seek its optimum position around the O atom. Refinement of all parameters, including a correction for isotropic extinction, gave a final *R* index of 7.2% and a *R_w* index of 7.6%. This relatively high final *R* index results from the twinned nature of the crystal and its influence on the absorption correction and from the deterioration of the crystal under the X-ray beam. The omission of 0*kl* reflections did not significantly improve the refinement. Final positional and displacement parameters are given in Table 2, observed and calculated structure factors in Table 3, selected interatomic distances and angles in Table 4, and a bond-valence analysis is given in Table 5.¹

TABLE 2. Atomic coordinates and displacement factors for sinkankasite

	<i>x</i>	<i>y</i>	<i>z</i>	<i>U</i> _{eq} (Å ²)	<i>U</i> ₁₁	<i>U</i> ₂₂	<i>U</i> ₃₃	<i>U</i> ₁₂	<i>U</i> ₁₃	<i>U</i> ₂₃
Mn	0.2887(2)	0.9520(2)	0.6821(2)	145(5)	240(9)	184(7)	39(5)	51(6)	54(5)	65(4)
P1	0.2971(3)	0.6566(2)	0.2606(3)	116(7)	186(12)	161(10)	41(8)	59(9)	41(7)	73(7)
P2	0.2914(3)	0.2566(2)	0.1038(3)	112(7)	187(12)	132(10)	38(8)	19(8)	40(7)	58(7)
Al1	1/2	1/2	1/2	82(12)	149(21)	123(18)	1(14)	30(13)	26(11)	56(11)
Al2	1/2	1/2	0	93(12)	190(21)	135(17)	1(14)	50(13)	49(12)	65(11)
O1	0.2899(8)	0.8156(7)	0.3614(8)	178(21)	328(39)	192(27)	72(22)	113(27)	80(23)	79(20)
O2	0.3909(7)	0.6426(6)	0.1003(7)	160(19)	312(36)	227(28)	23(20)	104(26)	97(21)	105(19)
O3	0.3476(7)	0.5873(6)	0.4219(7)	131(18)	225(32)	202(27)	22(19)	63(24)	49(20)	98(18)
O4	0.3857(7)	0.3101(6)	0.3259(8)	149(18)	261(34)	156(25)	41(20)	3(23)	29(21)	72(18)
O5	0.3458(7)	0.3474(6)	-0.0230(8)	163(19)	293(36)	183(26)	48(21)	21(25)	39(22)	102(19)
O6	0.2786(8)	0.0938(6)	0.9937(8)	170(20)	295(37)	172(27)	76(22)	53(26)	66(23)	77(19)
OH1	0.1363(8)	0.5740(8)	0.1438(10)	253(23)	211(37)	303(34)	240(30)	39(29)	-1(27)	125(26)
OH2	0.5789(6)	0.5165(6)	0.2761(7)	110(17)	190(30)	176(24)	1(18)	39(22)	36(19)	74(17)
OH3	0.1351(8)	0.2826(7)	0.1225(9)	205(21)	250(37)	224(29)	128(24)	-5(26)	52(23)	63(21)
OW1	0.2967(9)	0.7677(8)	0.7887(9)	270(26)	505(51)	274(34)	117(26)	155(34)	128(29)	121(24)
OW2	0.5186(9)	0.0040(9)	0.7596(12)	282(26)	255(41)	356(37)	354(35)	58(32)	71(31)	291(30)
OW3	0.2930(9)	0.1405(7)	0.5798(8)	229(23)	397(44)	232(31)	58(23)	23(30)	51(26)	71(21)
OW4	0.0573(6)	0.8887(9)	0.5972(12)	310(27)	291(44)	354(40)	308(35)	81(34)	121(32)	115(30)
OW5	0.0834(8)	0.9186(8)	0.1365(10)	242(23)	256(38)	307(34)	194(29)	53(29)	26(26)	145(25)
OW6	-0.0907(14)	0.5932(12)	0.4146(18)	613(46)	659(78)	542(60)	620(62)	-24(55)	222(56)	212(48)
H1	0.106(13)	0.470(2)	0.073(17)	300*						
H2	0.678(4)	0.547(12)	0.351(17)	300						
H3	0.063(9)	0.193(7)	0.055(17)	300						
H4	0.379(8)	0.737(14)	0.740(18)	300						
H5	0.290(15)	0.667(4)	0.710(16)	300						
H6	0.591(9)	0.071(10)	0.732(18)	300						
H7	0.580(11)	-0.041(12)	0.834(16)	300						
H8	0.397(1)	0.160(12)	0.613(18)	300						
H9	0.288(13)	0.233(7)	0.676(14)	300						
H10	0.015(12)	0.785(3)	0.545(17)	300						
H11	0.000(11)	0.947(11)	0.675(16)	300						
H12	0.139(12)	0.858(11)	0.186(16)	300						
H13	0.081(1)	0.998(9)	0.259(10)	300						
H14	-0.148(12)	0.527(9)	0.465(17)	300						
H15	-0.067(14)	0.510(9)	0.319(14)	300						

Note: displacement factors are multiplied by 10⁴.

* Fixed during refinement.

TABLE 4. Selected interatomic distances (Å) and angles (°) in sinkankasite

Mn-O1	2.195(5)	P2-O4	1.521(5)
Mn-OW1	2.158(8)	P2-O5	1.521(7)
Mn-OW4	2.137(8)	P2-OH3	1.578(8)
Mn-O6 ^a	2.188(6)	P2-O6 ^b	1.516(6)
Mn-OW2 ^a	2.120(8)	(P2-O)	1.534
Mn-OW3 ^a	2.170(8)		
(Mn-O)	2.161	Al1-O3 ^c	1.889(7) × 2
		Al1-O4 ^c	1.912(5) × 2
P1-O1	1.517(6)	Al1-OH2 ^c	1.861(6) × 2
P1-O2	1.521(7)	(Al1-O)	1.887
P1-O3	1.520(7)		
P1-OH1	1.573(7)	Al2-O2 ^d	1.904(7) × 2
(P1-O)	1.533	Al2-O5 ^d	1.884(6) × 2
		Al2-OH2 ^d	1.865(5) × 2
		(Al-O)	1.884
Mnφ₆ octahedron			
O1-OW1	3.101(10)	O1-Mn-OW1	90.8(2)
O1-OW4	3.014(12)	O1-Mn-OW4	88.2(3)
O1-OW2 ^a	3.051(8)	O1-Mn-OW2 ^a	90.0(3)
O1-OW3 ^a	3.068(9)	O1-Mn-OW3 ^a	89.3(2)
OW1-OW4	3.034(13)	OW1-Mn-OW4	89.9(3)
OW1-O6 ^a	3.118(9)	OW1-Mn-O6 ^a	91.7(2)
OW1-OW2 ^a	2.976(12)	OW1-Mn-OW2 ^a	88.1(3)
OW4-O6 ^a	3.052(8)	OW4-Mn-O6 ^a	89.8(3)
OW4-OW3 ^a	2.129(11)	OW4-Mn-OW3 ^a	93.2(3)
O6 ^a -OW2 ^a	3.104(11)	O6 ^a -Mn-OW2 ^a	92.2(3)
O6 ^a -OW3 ^a	3.035(9)	O6 ^a -Mn-OW3 ^a	88.3(2)
OW2 ^a -OW3 ^a	3.004(12)	OW2 ^a -Mn-OW3 ^a	88.9(3)
(O-O)	3.057	(O-Mn-O)	90.0
P1φ₄ tetrahedron			
O1-O2	2.497(9)	O1-P1-O2	110.6(4)
O1-O3	2.527(10)	O1-P1-O3	112.6(3)
O1-OH1	2.453(8)	O1-P1-OH1	105.1(4)
O2-O3	2.513(8)	O2-P1-O3	111.5(4)
O2-OH1	2.523(10)	O2-P1-OH1	109.2(3)
O3-OH1	2.496(9)	O3-P1-OH1	107.6(4)
(O-O)	2.501	(O-P1-O)	109.4
P2φ₆ tetrahedron			
O4-O5	2.508(8)	O4-P2-O5	111.1(3)
O4-OH3	2.498(9)	O4-P2-OH3	107.4(3)
O4-O6 ^b	2.510(6)	O4-P2-O6 ^b	111.5(4)
O5-OH3	2.481(10)	O5-P2-OH3	106.4(4)
O5-O6 ^b	2.517(9)	O5-P2-O6 ^b	111.9(3)
OH3-O6 ^b	2.508(10)	OH3-P2-O6 ^b	108.3(4)
(O-O)	2.504	(O-P2-O)	109.4
Al1φ₆ octahedron			
O3 ^c -O4 ^c	2.693(9) × 2	O3 ^c -Al1-O4 ^c	90.2(2) × 2
O3 ^c -OH2 ^c	2.681(9) × 2	O3 ^c -Al1-OH2 ^c	91.3(3) × 2
O3 ^c -O4 ^c	2.682(8) × 2	O3 ^c -Al1-O4 ^c	89.8(2) × 2
O3 ^c -OH2 ^c	2.621(8) × 2	O3 ^c -Al1-OH2 ^c	88.7(3) × 2
O4 ^c -OH2 ^c	2.672(9) × 2	O4 ^c -Al1-OH2 ^c	90.1(2) × 2
O4 ^c -OH2 ^c	2.665(6) × 2	O4 ^c -Al1-OH2 ^c	89.9(2) × 2
(O-O)	2.669	(O-Al1-O)	90.0
Al2φ₆ octahedron			
O2 ^d -O5 ^d	2.697(8) × 2	O2 ^d -Al2-O5 ^d	90.8(3) × 2
O2 ^d -OH2 ^d	2.669(9) × 2	O2 ^d -Al2-OH2 ^d	90.2(3) × 2
O2 ^d -O5 ^d	2.659(10) × 2	O2 ^d -Al2-O5 ^d	89.2(3) × 2
O2 ^d -OH2 ^d	2.662(7) × 2	O2 ^d -Al2-OH2 ^d	89.8(2) × 2
O5 ^d -OH2 ^d	2.679(7) × 2	O5 ^d -Al2-OH2 ^d	91.2(2) × 2
O5 ^d -OH2 ^d	2.623(9) × 2	O5 ^d -Al2-OH2 ^d	88.8(2) × 2
(O-O)	2.665	(O-Al2-O)	90.0
H bonding			
H1-OH1	0.96(3)	H1...OH3	2.02(7)
OH1-OH3	2.818(11)	OH1-H1-OH3	139(9)
H2-OH2	0.96(4)	H2...OW6 ^e	2.14(4)
OH2-OW6 ^e	3.054(14)	OH2-H2-OW6 ^e	161(6)
H3-OH3	0.96(7)	H3...OW5 ^f	1.71(7)
OH3-OW5 ^f	2.599(8)	OH3-H3-OW5 ^f	153(9)
H4-OW1	0.96(11)	H4...O4 ^c	2.46(9)
OW1-O4 ^c	3.409(11)	OW1-H4-O4 ^c	170(10)
H5-OW1	0.96(5)	H5...O3	2.09(12)

TABLE 4.—Continued

OW1-O3	2.761(8)	OW1-H5-O3	126(9)
H4-H5	0.95(14)	H4-OW1-H5	60(8)
H6-OW2	0.96(11)	H6...O1 ^e	1.81(11)
OW2-O1 ^e	2.760(11)	OW2-H6-O1 ^e	171(8)
H7-OW2	0.96(12)	H7...O6 ^a	1.89(12)
OW2-O6 ^a	2.837(11)	OW2-H7-O6 ^a	170(10)
H6-H7	1.47(18)	H6-OW2-H7	100(9)
H8-OW3	0.96(2)	H8...O2 ^c	2.61(7)
OW3-O2 ^c	3.379(8)	OW3-H8-O2 ^c	137(9)
H9-OW3	0.46(8)	H9...O5 ^h	1.95(8)
OW3-O5 ^h	2.757(7)	OW3-H9-O5 ^h	140(9)
H8-H9	1.41(14)	H8-OW3-H9	95(9)
H10-OW4	0.96(4)	H10...OW6	1.86(4)
OW4-OW6	2.807(13)	OW4-H10-OW6	170(3)
H11-OW4	0.96(11)	H11...OW5 ⁱ	1.91(11)
OW4-OW5 ⁱ	2.866(11)	OW4-H11-OW5 ⁱ	170(10)
H10-H11	1.61(11)	H10-OW4-H11	114(9)
H12-OW5	0.96(12)	H12...O1	1.90(12)
OW5-O1	2.808(11)	OW5-H12-O1	156(9)
H13-OW5	0.96(8)	H13...OW4 ^j	2.04(12)
OW5-OW4 ^j	2.866(11)	OW5-H13-OW4 ^j	142(10)
H12-H13	1.54(16)	H12-OW5-H13	106(9)
H14-OW6	0.97(12)	H14...O3 ^f	2.43(12)
OW6-O3 ^f	3.359(15)	OW6-H14-O3 ^f	161(9)
H15-OW6	0.96(9)	H15...OH1	2.55(13)
OW6-OH1	3.080(16)	OW6-H15-OH1	115(6)
H14-H15	1.35(18)	H14-OW6-H15	89(9)

Note: a = x, y + 1, z; b = x, y, z - 1; c = 1 - x, 1 - y, 1 - z; d = 1 - x, 1 - y, z; e = x + 1, y, z; f = x, 1 - y, z; g = 1 - x, y, 2 - z; h = x, y, z + 1; i = x, 2 - y, 1 - z; j = x, 1 - y, 1 - z.

DESCRIPTION OF THE STRUCTURE

MnO₂(H₂O)₄ and AlO₄(OH)₂ octahedra

The sinkankasite structure contains one symmetrically unique Mn position that is octahedrally coordinated by two O atoms and four H₂O groups. The H₂O groups are at the equatorial positions of the octahedron, which has a (Mn-O) distance of 2.161 Å and bond lengths ranging from 2.120 to 2.195 Å. Peacor et al. (1984) reported chemical analyses for sinkankasite from the Barker pegmatite. The material they studied contains significant Fe²⁺; the ratio of Mn²⁺ to Fe²⁺ at this site is about 1.0 to 0.6. The Mn²⁺ and Fe²⁺ species have very similar X-ray scattering factors, and it is not possible to refine their ratios directly using X-ray data. However, the sums of the empirical radii of Shannon (1976) for ⁶Mn²⁺, ⁶Fe²⁺, and ¹³O²⁻ are 2.19 and 2.14 Å for the Mn²⁺-O and Fe²⁺-O bonds, respectively. The (Mn-O) bond length of 2.161 Å reported here is consistent with the occurrence of both Mn²⁺ and Fe²⁺ at this site.

The structure has two symmetrically distinct Al positions, and both occur on a center of symmetry. Each Al is octahedrally coordinated by four O atoms and two OH groups, and the latter are in a trans arrangement. The (Al1-O) and (Al2-O) distances are 1.887 and 1.884 Å, respectively, fairly close to the sum of the ionic radii for ⁶Al, ¹³O, and ¹²OH (0.535 + 1.353 = 1.888 Å; Shannon,

¹ A copy of Table 3 may be ordered as Document AM-95-588 from the Business Office, Mineralogical Society of America, 1130 Seventeenth Street NW, Suite 330, Washington, DC 20036, U.S.A. Please remit \$5.00 in advance for the microfiche.

TABLE 5. Bond-valence analysis (vu) for sinkankasite

	O1	O2	O3	O4	O5	O6	OH1	OH2	OH3	OW1	OW2	OW3	OW4	OW5	OW6	Σ
Mn	0.335					0.341				0.370	0.410	0.358	0.391			2.205
Al1			0.526 ^{x2} ↓	0.494 ^{x2} ↓				0.567 ^{x2} ↓								3.174
Al2		0.505 ^{x2} ↓			0.533 ^{x2} ↓			0.561 ^{x2} ↓								3.198
P1	1.310	1.296	1.300				1.126									5.032
P2				1.296	1.296	1.314			1.111							5.017
H1							0.85		0.15							1.0
H2								0.90							0.10	1.0
H3									0.80					0.20		1.0
H4				0.05						0.95						1.0
H5			0.12							0.88						1.0
H6	0.20										0.80					1.0
H7						0.20					0.80					1.0
H8		0.05										0.95				1.0
H9					0.15							0.85				1.0
H10													0.80		0.20	1.0
H11													0.80	0.20		1.0
H12	0.20													0.80		1.0
H13													0.15	0.85		1.0
H14			0.05												0.95	1.0
H15							0.05								0.95	1.0
Σ	2.045	1.851	1.996	1.840	1.979	1.855	2.026	2.028	2.061	2.200	2.010	2.158	2.141	2.050	2.200	

* Bond-valence parameters from Brown and Altermatt (1985).

1976). Thus, both the site scattering and the observed $\langle \text{Al-O} \rangle$ distances are consistent with complete occupancy of Al1 and Al2 by Al, as indicated by the electron-microprobe analysis of Peacor et al. (1984).

PO₃OH tetrahedra

There are two symmetrically distinct P positions in sinkankasite. Each P is tetrahedrally coordinated by three O atoms and an OH group, thus forming acid phosphate groups. The $\langle \text{P1-O} \rangle$ and $\langle \text{P2-O} \rangle$ distances are 1.533 and 1.534 Å, respectively. The tetrahedra show significant bond-length distortion, with bond lengths ranging from 1.517 to 1.573 Å and 1.516 to 1.578 Å in the P1 ϕ_4 (ϕ = unspecified ligand) and P2 ϕ_4 tetrahedra, respectively; in each case, the longest bond is to the OH group, as is usually observed for acid phosphate groups because of local bond-valence requirements around the acid ligand (Table 5).

Structure topology

The Al ϕ_6 octahedra share one set of trans vertices to form an Al ϕ_5 chain extending along the *c* direction. Equatorial vertices of each chain are linked by P ϕ_4 tetrahedra (Fig. 1a) to form a heteropolyhedral chain of stoichiometry Al(PO₃OH)₂(OH). These chains are cross-linked into sheets of the form Mn²⁺(H₂O)₄[Al(PO₃OH)₂(OH)] by linkage of the trans vertices of the Mn²⁺ ϕ_6 octahedra with vertices of P ϕ_4 tetrahedra of adjacent chains (Fig. 2). These sheets lie in the (100) plane and are cross-linked into a three-dimensional structure by a network of H bonds (Fig. 3); this arrangement accounts for the perfect {100} cleavage of sinkankasite (Peacor et al., 1984).

H bonding

The H atom positions obtained by constrained least-squares refinement of the positional parameters are rea-

sonable, both in terms of donor and acceptor bond lengths and bond angles (Table 4) and the bond-valence requirements of the donor and acceptor anions (Table 5). There are 15 symmetrically unique H positions in sinkankasite, and H bonding plays two distinct roles in the structure: (1) H bonds bridge between the heteropolyhedral sheets and the interlayer anions, providing the only linkage be-




Fig. 1. (a) The Al(PO₃OH)₂(OH) chain in sinkankasite; Al ϕ_6 octahedra are shown by irregular dot shading; P ϕ_4 tetrahedra are shaded with crosses; (b) the type VI chain of Moore (1970), showing the octahedral chain viewed down its length, with the relative heights of the tetrahedra shown as fractions of the chain-axis length of ~ 7 Å.




Fig. 2. The $\text{Mn}^{2+}(\text{H}_2\text{O})_4[\text{Al}(\text{PO}_3\text{OH})_2(\text{OH})]$ sheet in the structure of sinkankasite; MnO_6 octahedra are shaded with dashed lines; other polyhedral shadings are as in Fig. 1.




Fig. 3. The structure of sinkankasite projected down $[001]$; shadings as in Fig. 2; interstitial H_2O groups shown by shaded circles.

tween sheets, and (2) H bonding occurs within the heteropolyhedral sheets.

There are eight H positions that provide linkage between the heteropolyhedral sheets and the interlayer OW5 and OW6 positions (Fig. 4). These H positions participate in the following bonds: $\text{OH2-H2}\cdots\text{OW6}^e$, $\text{OH3-H3}\cdots\text{OW5}^f$, $\text{OW4-H10}\cdots\text{OW6}$, $\text{OW4-H11}\cdots\text{OW5}^i$, $\text{OW5-H12}\cdots\text{O1}$, $\text{OW5-H13}\cdots\text{OW4}^j$, $\text{OW6-H14}\cdots\text{O3}^j$, and $\text{OW6-H15}\cdots\text{OH1}$. Acceptor distances range from 1.71 Å (strong) to 2.55 Å (weak).

Each of the OW5 and OW6 anions bond to four H atoms. The OW5 anion donates the $\text{OW5-H12}\cdots\text{O1}$ and $\text{OW5-H13}\cdots\text{OW4}^j$ bonds, one of which bonds to the heteropolyhedral sheet on either side, with acceptor distances of 1.90 and 2.04 Å, respectively. The OW5 position also accepts the $\text{OH3-H3}\cdots\text{OW5}^f$ and $\text{OW4-H11}\cdots\text{OW5}^i$ bonds, with acceptor distance of 1.71 and 1.91 Å, respectively, and each of these bonds is to the same heteropolyhedral sheet (Fig. 4).

The OW6 anion donates the $\text{OW6-H14}\cdots\text{O3}^j$ and $\text{OW6-H15}\cdots\text{OH1}$ bonds, one of which bridges to the heteropolyhedral sheet on the other side, with acceptor distances of 2.43 and 2.55 Å, respectively, which indicate weak interactions only. The OW6 anion accepts a H bond from each adjacent sheet; the fairly strong $\text{OH2-H2}\cdots\text{OW6}^e$ and $\text{OW4-H10}\cdots\text{OW6}$ bonds have acceptor distances of 2.14 and 1.86 Å, respectively.

Seven H positions participate in H bonds between two anions of the same heteropolyhedral sheet (Fig. 5). These bonds are as follows: $\text{OH1-H1}\cdots\text{OH3}$, $\text{OW1-H4}\cdots\text{O4}^e$, $\text{OW1-H5}\cdots\text{O3}$, $\text{OW2-H6}\cdots\text{O1}^e$, $\text{OW2-H7}\cdots\text{O6}^g$, $\text{OW3-H8}\cdots\text{O2}^e$, and $\text{OW3-H9}\cdots\text{O5}^h$, with acceptor distances

ranging from 1.81 to 2.61 Å. These H bonds increase the sheet rigidity and satisfy the bond-valence requirements of the donor and acceptor anions.

General structural relations

The principal structure motif in sinkankasite is the $\text{Al}(\text{PO}_3\text{OH})_2\text{OH}$ chain that we can generalize to the form $\text{M}(\text{T}\phi_4)_2\phi$, where M is an octahedrally coordinated cation and T is a tetrahedrally coordinated cation. In a paper of fundamental importance, Moore (1970) considered the structural hierarchy of octahedral-tetrahedral chains based on an $\text{M}\phi_5$ backbone. He developed a hierarchy of all possible arrangements with a chain of repeat distance of ~ 7.2 Å and showed that there is a fairly large family of minerals based on these chains.

Sinkankasite has the type VI chain (Fig. 1b) of Moore (1970), designated as the tancoite chain by Hawthorne (1985). This chain is found in a number of structures (Table 6), all of which show the typical ~ 7.2 -Å repeat (6.9–7.3 Å), except for tancoite, which has a doubled repeat distance of 14.07 Å. Sinkankasite shows most affinity with the segelerite-group structures. The latter are treated in some detail by Moore and Araki (1977), who show the relationship of segelerite to jahnsite in terms of cross linkage of dense $\text{X}^{2+}\text{M}^{3+}(\text{PO}_4)_2\text{OH}$ slabs by $\text{M}^{2+}\text{O}_2(\text{H}_2\text{O})_4$ octahedra. The solution of the sinkankasite structure raises another aspect of geometrical isomerism (Hawthorne, 1983a) with regard to these structures. Sinkankasite consists of slabs constructed from $\text{M}(\text{T}\phi_4)_2\phi$ chains that are cross-linked by $\text{MO}_2(\text{H}_2\text{O})_4$ octahedra, and there is ample opportunity for geometrical isomerism in this general type of arrangement. The possibilities are investigated in Figure 6 for repeat distances of one (~ 9 Å) or two (~ 18 Å) chains in the direction of linkage. As is apparent from Figure 1, the $\text{M}\phi_5$ chain is modulated such




Fig. 4. The structure of sinkankasite projected down [001], showing intersheet H bonds. Al atoms are stippled, Mn atoms are crosshatched, P atoms are parallel ruled, O atoms are shaded in the lower left corner, and H atoms are given as small open circles. Donor H and acceptor H bonds are drawn as heavy solid and broken lines, respectively.




Fig. 5. The structure of sinkankasite projected down [100], showing intrasheet H bonds; legend as in Fig. 4.

TABLE 6. Minerals based on the type VI $M(T\phi_4)_2\phi$ chain of Fig. 1

Mineral	Formula	<i>a</i> (Å)	<i>b</i> (Å)	<i>c</i> (Å)	β (°)	Sp. Gr.	Reference
Tancoite	$Na_2Li[Al(PO_4)_2(OH)]H$	6.948(2)	14.089(4)	14.065(3)		<i>Pbcb</i>	1
Sideronatrite*	$Na_2[Fe^{3+}(SO_4)_2(OH)] \cdot 3H_2O$	7.29(1)	20.56(2)	7.17(2)		<i>Pnr2</i>	2
Jahnsite	$CaMnMg_2[Fe^{3+}(PO_4)_2(OH)]_2 \cdot 8H_2O$	14.94(2)	7.14(1)	9.93(1)	110.16(8)	<i>P2/a</i>	3
Whiteite	$CaFe^{2+}Mg_2[Al(PO_4)_2(OH)]_2 \cdot 8H_2O$	14.90(4)	6.98(2)	10.13(2)	113.11(9)	<i>P2/a</i>	4
Lun'okite	$Mn_2(Mg,Fe^{2+},Mn)_2[Al(PO_4)_2(OH)]_2 \cdot 8H_2O$	14.95	18.71	6.96		<i>Pbca</i>	—
Overite	$Ca_2Mg_2[Al(PO_4)_2(OH)]_2 \cdot 8H_2O$	14.72(1)	18.75(2)	7.107(4)		<i>Pbca</i>	5
Segelerite	$Ca_2Mg_2[Fe^{3+}(PO_4)_2(OH)]_2 \cdot 8H_2O$	14.826(5)	18.751(4)	7.307(1)		<i>Pbca</i>	5
Wilhemvierlingite	$Ca_2Mn_2[Fe^{3+}(PO_4)_2(OH)]_2 \cdot 8H_2O$	14.80(5)	18.50(5)	7.31(2)		<i>Pbca</i>	—
Sinkankasite	$Mn^{2+}(H_2O)_4[Al(PO_4)_2(OH)](H_2O)_2$	9.590(2)	9.818(2)	6.860(1)	99.63(3)	<i>P1</i>	6
Guildite	$Cu^{2+}[Fe^{3+}(SO_4)_2(OH)] \cdot 4H_2O$	9.786(2)	7.134(1)	7.263(1)	105.38(1)	<i>P2_1/m</i>	7
Yftsite	$Y_4Ti(SiO_4)_2O(F,OH)_6$	14.949(4)	10.626(2)	7.043(2)		<i>Cmcm</i>	8

Note: references are as follows: 1 = Hawthorne (1983b); 2 = Scordari (1981); 3 = Moore and Araki (1974); 4 = Moore and Ito (1978); 5 = Moore and Araki (1977); 6 = this study; 7 = Wan et al. (1978); 8 = Balko and Bakakin (1975).

* Structure not definitively established.

that tetrahedra can link to vertices of adjacent octahedra. This modulation can occur orthogonal to or in the plane of the sheet formed by the $M(T\phi_4)_2\phi$ chains and their linking $MO_2(H_2O)_4$ octahedra. It is this difference in modulation orientation that combines with the cis and trans possibilities of the linking $MO_2(H_2O)_4$ octahedra to give the possible arrangements of Figure 6. We may divide them into three groups: (1) those arrangements with

the modulation orthogonal to the sheet and only one type of octahedral cross-linkage (Fig. 6a and 6b), where Figure 6a corresponds to the arrangement in sinkankasite, (2) those arrangements with the modulation in the plane of the sheet (Fig. 6c and 6d), corresponding to the arrangements in the hypothetical structure in Figure 4c of Moore and Araki (1977) and segelerite, respectively, and (3) those arrangements with both modulations present (Fig. 6e and




Fig. 6. Possible topologies involving $M(T\phi_4)_2\phi$ chains (viewed end-on and represented as squares) cross-linked by $M\phi_6$ octahedra with the linkages in cis (M_c) or trans (M_t) arrangements, with the modulation direction of the $M(T\phi_4)_2\phi$ chains taken into account; the heights of the tetrahedral linkages are given by symbols 1 ($=\frac{1}{4}$) and 3 ($=\frac{3}{4}$), which are the approximate z coordinates of the T cations for a chain-repeat length of ~ 7 Å and M cations

at $z = 0$ and $\frac{1}{2}$; (a) modulation orthogonal to the sheet and only trans linkages (sinkankasite); (b) modulation orthogonal to the sheet and only cis linkages (not yet known); (c) modulations in the plane of the sheet and only trans linkages (hypothetical structure of Moore and Araki, 1977); (d) modulation in the plane of the sheet and only cis linkages (segelerite, overite); (e), (f) mixed modulations and mixed linkages (not yet known).

6f) (these have not yet been found in crystals). Thus we have a coherent hierarchy of arrangements, two of which have so far been found in structural arrangements of minerals.

ACKNOWLEDGMENTS

This work was supported by the Natural Sciences and Engineering Research Council of Canada in the form of Operating, Infrastructure and Major Equipment grants to F.C.H.

REFERENCES CITED

- Balko, V.P., and Bakakin, V.V. (1975) The crystal structure of the natural yttrium and rare-earth fluoritino-silicate $(Y,Tr)_4(F,OH)_8TiO(SiO_4)_2$ (Yfsite). *Zhurnal Strukturnoi Khimii*, 16, 837–842.
- Brown, I.D., and Altermatt, D. (1985) Bond-valence parameters obtained from a systematic analysis of the inorganic crystal structure database. *Acta Crystallographica*, B41, 244–247.
- Cromer, D.T., and Liberman, D. (1970) Relativistic calculation of anomalous scattering factors for X rays. *Journal of Chemical Physics*, 53, 1891–1898.
- Cromer, D.T., and Mann, J.B. (1968) X-ray scattering factors computed from numerical Hartree-Fock wave functions. *Acta Crystallographica*, A24, 321–324.
- Hawthorne, F.C. (1983a) Graphical enumeration of polyhedral clusters. *Acta Crystallographica*, A39, 724–736.
- (1983b) The crystal structure of tancoite. *Tschermaks mineralogisch-petrographische Mitteilungen*, 31, 121–135.
- (1985) Towards a structural classification of minerals: the $^{VI}M^{IV}T_2\phi_n$ minerals. *American Mineralogist*, 70, 455–473.
- Moore, P.B. (1970) Structural hierarchies among minerals containing octahedrally coordinating oxygen: I. Stereoisomerism among corner-sharing octahedral and tetrahedral chains. *Neues Jahrbuch für Mineralogie Monatshefte*, 163–173.
- Moore, P.B., and Araki, T. (1974) Jahnsite, $CaMn^{2+}Mg_2(H_2O)_8Fe_3^{3+}(OH)_2[PO_4]_4$: A novel stereoisomerism of ligands about octahedral corner-chains. *American Mineralogist*, 59, 964–973.
- (1977) Overite, segelerite, and jahnsite: A study in combinational polymorphism. *American Mineralogist*, 62, 692–702.
- Moore, P.B., and Ito, J. (1978) Whiteite, a new species, and a proposed nomenclature for the jahnsite-whiteite complex series. *Mineralogical Magazine*, 42, 309–316.
- Peacor, D.R., Dunn, P.J., Roberts, W.L., Campbell, T.J., and Simmons, W.B. (1984) Sinkankasite, a new phosphate from the Barker pegmatite, South Dakota. *American Mineralogist*, 69, 380–382.
- Scordari, F. (1981) Sideronatrite: A mineral with a $\{Fe_2(SO_4)_4(OH)_2\}$ guildite type chain. *Tschermaks mineralogisch-petrographische Mitteilungen*, 28, 315–319.
- Shannon, R.D. (1976) Revised effective ionic radii and systematic studies of interatomic distances in halides and chalcogenides. *Acta Crystallographica*, A32, 751–767.
- Wan, C., Ghose, S., and Rossman, G.R. (1978) Guildite, a layer structure with a ferric hydroxy-sulphate chain and its optical absorption spectra. *American Mineralogist*, 63, 478–483.

MANUSCRIPT RECEIVED SEPTEMBER 1, 1994

MANUSCRIPT ACCEPTED JANUARY 9, 1995